

Client: Antique Ceilings

Date: 9/30/13

Project Number: 101358578SAT-001A

Test Number: 4

Operator: EG-JCM

Specimen Info: "PVC Decorative Ceiling Tiles" were self-supporting.

TEST RESULTS

FLAMESPREAD INDEX: 0

SMOKE DEVELOPED INDEX: 80

SPECIMEN DATA . . .

Time to Ignition (sec): 9

Time to Max FS (sec): 0

Maximum FS (feet): 0.0

Time to 980 F (sec): Never Reached

Time to End of Tunnel (sec): Never Reached

Max Temperature (F): 552

Time to Max Temperature (sec): 600

Total Fuel Burned (cubic feet): 46.00

FS*Time Area (ft*min): 0.2

Smoke Area (%A*min): 66.6

Unrounded FSI: 0.1

CALIBRATION DATA . . .

Time to Ignition of Last Red Oak (Sec): 56.0

Red Oak Smoke Area (%A*min): 84.5